## **Jampilen RP340N**

**کـوثر شیـمی** Kosar Shimi +9821 - 43462000 info@kosar.co www.kosar.co

"Jampilen RP340N" is a polypropylene random copolymer which features extremely high flow properties, excellent

transparency, high gloss and exhibits good antistatic properties. "Jampilen RP340N" is mainly designed for transparent



Random Copolymer

**Description:** 

housewares and quality packaging applications. It is an outstanding grade for injection molded containers and thin-walled packaging where clarity is of utmost importance. In many of these applications, "Jampilen RP340N" can replace PS since it can match the optical properties whilst adding low weight, low odor transfer, chemical resistance and impact strength. cessing Method: Injection molding Extrusion (Sheet) Hea/tures High flow properties Excellent transparency High gloss Good antistatic properties Randorn copolymer **Typical Application** Injection molded containers and thin-walled packaging Clear containers Household articles Packaging for food, cosmetics and pharmaceutical products Lide caps and closures Coextrusion with other polypropylene resins to produce multilayer sheet for thermeforming trays for fresh pasta and bakery products **Approval:** Food VALUE **TYPICAL PROPERTIES METHOD** UM **Physical** Melt Flow Rate (230 °C, 2.16kg) ASTM D1238 g/10min 11 ASTM D1505 Density 0.9 g/cm<sup>2</sup> **Mechanical** Flexural Modulus 1050 MPa ASTM D790 Tensile Strength at Yield 28 MPa ASTM D638 Tensile Elongation at Yield 12 % ASTM D638 Izod Impact Strength (notched) at 23 °C 85 ASTM D256 J/m **Rockwell Hardness** 94 R Scale ASTM D785 Thermal Vicat softening point (10N) 128 °C **ASTM D1525** °C H.D.T. (0.46 Mpa) 83 ASTM D648 Accelerated oven ageing in air at 150 °C hours 360 ASTM D3012 **Optical** 9 Haze (1 mm) % **ASTM D1003**  $Gloss(60^{\circ})$ 85 **ASTM D2457** 

4th Floor, No. 68, Taban St., Africa Blvd., Tehran, Iran.

Tel: +9821-84286, Fax: +9821-88879811

Email: info@jppc.ir

www.jppc.ir

This data and information is considered to be correct and offered in good faith as a guide. But we do not warrant or otherwise guarantee the merchantability, fitness for a particular purpose or suitability of this information, products or processes described.