Page:1/1

شد کرد و میمی تبر وز	TYPICAL DATA SHEET* GRADE	ISSUE DATE	Jul-17 <u>VW.TPCO.IR</u>	<b>کوتـرشيـمی</b> Kosar Shimi +9821 - 43462000
	HIPS7240	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612		info@kosar.co www.kosar.co

HIPS7240 is a very high impact polystyrene for the extrusion industry. This grade has been designed to diluted with crystal polystyrene.

The good melt strength of this grade makes it particularly suited for deep-draw thermoforming.

HIPS7240 is available in white color.

Applications:

darty sheet, cups, trays, egg boxes, general packaging, coextrusion with GPPS at industrial sheets. food containers

PROPERTY	UNIT (	TESTMETHOD	TYPICAL VALUE		
MELT FLOW INDEX(200°C-5KG)	g/10min	ASTM D-1238	4.5		
STYRENE RESIDUAL MONOMER	PPM	CLG LABPSG004 (ATOFINA TEST METHOD)	<500		
VICAT SOFTENING POINT ( 50 °C/hr 1kg)	°C	ASTMD-1525	97		
ROCKWELL HARDNESS	-	ASTM D-785	SCALE/R65		
TENSILE STRESS AT YEILD	MPA	ASTM D-638	23		
TENSILE STRESS AT BREAK	MPA	ASTM D-638	21		
ELONGATION AT BREAK	%	ASTM D-638	60		
TENSILE MODULUS	MPA	ASTM D-638	1950		
IZOD IMPACT	KJ/M2	ISO180	1		

\* All above mentioned data are typical values and not to be construed as real specifications. Users should confirm results by their own tests. For more information about guaranteed items, please refer to S.S.S. (Standard Sales Specifications)

Density and shrinkage of this grade are approximately around 1.04 kg/lit & (0.4-0.7)%(ASTM D-955) respectively.

All test are carried out at 23°C , unless otherwise stated.

If in grade reference the fourth digit is "1"(7241) ,indicates an external lubricants is included.