

HYOSUNG POLYPROPYLENE

PRODUCT DATA SHEET

TOPILENE® J740

کوثر شیمی

Kosar Shimi

+9821 - 43462000

info@kosar.co

www.kosar.co

● CHARACTERISTICS

TOPILENE® J740 is a well designed block copolymer that features high flowability and balanced mechanical properties suitable for injection molding applications

- ◇ High flowability
- ◇ Good stiffness
- ◇ High Impact Strength
- ◇ UL 94HB

● PROCESS GUIDE LINE

Require no pre-drying before processing. But moisture might give a bad molding condition and make some quality problems. If it has any moisture, it would be needed pre-drying.
(drying condition : 80~100°C / 2~4hrs at air circulated condition)

- ◇ Injection Temp : 190~220°C
- ◇ Injection Pressure : 800~1000 bar

● PROPERTIES

PROPERTY	ASTM METHOD	UNIT	VALUE
Density	D792	g/cm ³	0.90
Melt Flow Index	D1238	g/10min	25.0
Tensile Strength	D638	kg/cm ²	270
Flexural Modulus	D790	kg/cm ²	14,000
Izod Impact Strength at 23°C / -10°C	D256	kg · cm/cm	6.5 / 4.0
Rockwell Hardness	D785	R-Scale	90
Heat Deflection Temp	D648	°C	110
Remark			Impact strength Flowability, UL 94HB

* The data listed here is typical value not for the specification warranty.

● APPLICATIONS

- ◇ General purpose
- ◇ Industrial Parts (Big size container etc)
- ◇ Electric appliances (Washing M/C parts-Under base, Outer tub etc)

بازرگانی کوثر

Kosar Trading

+9821-88174517

info@kosar.co

www.kosar.co