

## KD CHEM CO., LTD.

OFFICE: 234, HAEAN-RO, DANWON-GU, ANSAN-SI, GYEONGGI-DO, KOREA

TEL: 82 31 493 6882 FAX: 82 31 492 9860 www.kdchem.co.kr

كوثرشيـمى Kosar Shimi +9821 - 43462000 info@kosar.co www.kosar.co

LX - 700

POSIZION

g-12-7-n organic liquid complex

PHYSICAL PROPERTIES

Appearance

Specific Gravity (252

Refractive Index (25°

Viscosity (25°C)

Reddish-yellowish transparent liquid

 $1.016 \pm 0.03$ 

1,481\ ± 0.01

: Max/150 m.Pa.s

## **CHARACTERISTICS**

LX-700 provides excellent heat stability and witigil color

Heat stability will be improved when used with popyidized spybean oil.

Provides excellent anti plate-out properties, along with anti-broming

and anti-bleeding properties.

Recommended dosage is about 1.5 ~ 3.0 phr

## **APPLICATION**

General purpose, including soft and semi-rigid PVC film or sheet and extrusion.

## PACKING

200kgs / DRUM