



HYUNDAI ENGINEERING PLASTICS

بازرگانی کوثر

Kosar Trading

+9821-88174517

info@kosar.co

www.kosar.co

Product Information

SOLARENE[®] GPPS, G-144

Description

SOLARENE[®] G-144 is a medium strength, good flow general purpose polystyrene mainly for Injection molding. It is particularly useful for blend with high impact polystyrene in heat contact applications.

Applications

SOLARENE[®] G-144 is useful to home electric parts, toys and miscellaneous goods etc.

Supplied and storage

SOLARENE[®] G-144 should be kept in its original packages in cool and dry place. Avoid direct exposure to sunlight. **SOLARENE[®]** G-144 can be stored in silos.

Food contact

The composition of **SOLARENE[®]** G-144 complies with 21CFR.SEC.177.1640 in FDA regulations, Ministry of Health and Welfare Notification NO. 370 in Japan, KFDA Notification NO. 98-60 in Korea.

Standard properties

The statement in the document are based on our present technical knowledge, experience and data selected from the literature. All tests carried out at 23°C unless otherwise stated by own test methods. Mechanical properties are measured on injection molded tests specimens. Neither do they imply any binding assurance of stability for a particular purpose.

>>Typical Value for Product

HYUNDAI-EP

QA630-31113



HYUNDAI ENGINEERING PLASTICS

بازرگانی کوثر
Kosar Trading
+9821-88174517
info@kosar.co
www.kosar.co

Typical Value for Product

SOLARENE[®] GPPS, G-144

Test item	Unit	Test method		Typical value	
		ISO	ASTM	ISO	ASTM
<u>Mechanical properties</u>					
Tensile stress at yield	MPa	527	D638		48
Tensile stress at break	MPa	527	D638		48
Tensile strain at yield	%	527	D638		-
Tensile strain at break	%	527	D638		2
Young's modulus	MPa	527	D638		2,300
Flexural strength	MPa	178	D790		88
Flexural modulus	MPa	178	D790		3,380
Charpy impact strength(23°C/-30°C)	kJ/m ²	179	-		-
Charpy notched impact strength(23°C/-30°C)	kJ/m ²	179	D6110		-
IZOD impact notched strength(23°C)	kJ/m ²	180	D256		-
IZOD impact notched strength(-23°C)	kJ/m ²	180	D256		-
Rockwell hardness(L scale)	-	2039	D785		100
<u>Rheological Properties</u>					
Melt flow index(200°C-5kg)	g/10min	1133	D1238		8.5
Molding shrinkage(along chain)	%	Injection	Injection		.5
Molding shrinkage(across chain)	%	injection	injection		.4
<u>Thermal properties</u>					
VICAT softening temp., (B/50)	°C	306	D1525		97
Heat distortion temp., (1.8MPa)	°C	75	D648		77
<u>Optical properties</u>					
Haze(Injection Mold Specimen)	%		D1003	-	0.4
Yellow index(Pellets)	-		D1925	-	-4.5
<u>Burning properties</u>					
Flammability, 1.6t	Class		UL94		HB
3.2t	Class		UL94		HB

HYUNDAI-EP

QA630-31113



HYUNDAI ENGINEERING PLASTICS

بازرگانی کوثر

Kosar Trading

+9821-88174517

info@kosar.co

www.kosar.co

Typical Value for Product

SOLARENE[®] GPPS, G-144

Items	Specification	Typical value
<u>Material Test</u>		
lead, ppm	less than 100	less than 1
cadmium, ppm	less than 100	less than 1
<u>Volatiles</u>		
styrene, ppm		300
toluene, ppm	less than	non detected
ethylbenzene, ppm	5,000	50
iso-propylbenzene, ppm	as total amount	non detected
n-propylbenzene, ppm		non detected
<u>Extraction Test</u>		
heavy metals as Pb, ppm	less than 1	non detected
evaporation residue		
n-heptane, ppm	less than 240	9
20% ethanol, ppm	less than 30	5
distilled water, ppm	less than 30	2
4% acetic acid, ppm	less than 30	1
KMnO4 consumption, ppm	less than 10	1

Note

1. SOLARENE G-144 Grade comply with CFR21.177.1640 in FDA, Ministry of Health and Welfare Notification NO. 370 in Japan, KFDA Notification NO. 98-60 in Korea.
2. The statement in the document are based on our present technical knowledge experience.

HYUNDAI-EP

QA630-31113