

Grade/Product Name : 7260 (THG-S :Grade)



کوثر شیمی
Kosar Shimi
+9821 - 43462000
info@kosar.co
www.kosar.co

| Test/Composition | value | Unit | Method |
|------------------------------------|-------------|---------|------------|
| Density | 0.962±0.002 | g/cm3 | ISO 1183 |
| FRR (5/2/16 ¹) | 2.9±0.5 | | |
| MFR (190°/2.16) | 8±2 | g/10min | ISO 1133 |
| MFR (190°/5) | 23±3 | g/10min | ISO 1133 |
| Notched Impact (23°C) ² | ≥4 | mJ/mm2 | ISO179/1eA |

Main Application: Injection moulding

Product Type: Homopolymer

Notes:

- 1- FRR values are statistical and calculated by dividing MFR values.
- 2- Notch Impact Test specimen from compressed moulded sheet 23°C and The data quoted is average values