

**Grade/Product Name : HF4760(THE/THT:Grade)**



کوثر شیمی

Kosar Shimi

+9821 - 43462000

info@kosar.co

www.kosar.co

Test/Composition	value	Unit	Method
Density	0.95 6 ±0.002	g/cm <sup>3</sup>	ISO 1183
MFR(190°/21.16)	23±4	g/10min	ISO 1133
MFR(190°/5)	1.2±0.3	g/10min	ISO 1133
Notched Impact (23°C) <sup>2</sup>	≥9	mJ/mm <sup>2</sup>	ISO179/1eA

**Main Application: Small blow moulding**

**Notes:**

**1- FRR values are statistical and calculated by dividing MFR values.**

**2- Notch Impact Test specimen from compressed moulded sheet 23°C and The data quoted is average values**