

# Jampilen HP552R

## Homopolymer



### Description:

"Jampilen HP552R" is a high melt flow homopolymer for the production of CF, BCF and fine denier staple fibers at medium to high spinning speeds and exhibits excellent antigasfading properties.

"Jampilen HP552R" is suitable for nonwoven fabrics for diapers, medical-sanitary applications and wipes. Another typical application is high tenacity continuous filament for straps for backpacks, sport bags, bulk bags and safety belts. Continuous filament with medium tenacity is used for upholstery and sportswear. "Jampilen HP552R" is also suited for the production of bulked continuous filament for carpets.

"Jampilen HP552R" is suitable for food contact.

### Processing Method:

Fiber Extrusion (CF, BCF, staple)

### Features:

High melt flow  
Excellent antigasfading properties  
Good processability  
Homopolymer

### Typical Applications:

Nonwoven fabrics for diapers, medical-sanitary applications  
Wipes and tissues  
Straps for backpacks, sport bags, bulk bags and for safety belts  
Upholstery and sportswear  
Bulk continuous filament for carpets  
Nonwoven staple fiber  
Hygiene nonwoven

### Approval:

Food

TYPICAL PROPERTIES	VALUE	UNIT	METHOD
<b>Physical</b>			
Melt Flow Rate (230 °C, 2.16kg)	25	g/10min	ASTM D1238
Density	0.9	g/cm <sup>3</sup>	ASTM D1505
<b>Mechanical</b>			
Flexural Modulus	1500	MPa	ASTM D790
Tensile Strength at Yield	32	MPa	ASTM D638
Tensile Elongation at Yield	13	%	ASTM D638
Izod Impact Strength (notched) at 23 °C	30	J/m	ASTM D256
Rockwell Hardness	100	R Scale	ASTM D785
<b>Thermal</b>			
Vicat softening point (10N)	152	°C	ASTM D1525
H.D.T. (0.46 Mpa)	94	°C	ASTM D648
Accelerated oven ageing in air at 150 °C	150	hours	ASTM D3012