

Grade/Product Name : 7260 (THG-S :Grade)



کوثر شیمی  
Kosar Shimi  
+9821 - 43462000  
info@kosar.co  
www.kosar.co

Test/Composition	value	Unit	Method
Density	0.962±0.002	g/cm3	ISO 1183
FRR (5/2/16 <sup>1</sup> )	2.9±0.5		
MFR (190°/2.16)	8±2	g/10min	ISO 1133
MFR (190°/5)	23±3	g/10min	ISO 1133
Notched Impact (23°C) <sup>2</sup>	≥4	mJ/mm2	ISO179/1eA

Main Application: Injection moulding

Product Type: Homopolymer

Notes:

- 1- FRR values are statistical and calculated by dividing MFR values.
- 2- Notch Impact Test specimen from compressed moulded sheet 23°C and The data quoted is average values