



NAVID ZAR CHIMI Ind. Co.
Polypropylene Manufacturer



Parslen ZB332L

Parslen ZB332L Is a Heterophasic Polypropylene Copolymer Designed for Injection Moulding Battery Cases and Technical Items.

کوثر شیمی
Kosar Shimi
+9821 - 43462000
info@kosar.co
www.kosar.co

Product Description

- This grade offers an excellent balance of mechanical properties and process ability and features an excellent long-term heat stability
- Articles moulding with Parslen ZB332L offer a good balance of stiffness and toughness, good surface properties and a very high resistance to chemicals and crazing.

Application:

- Parslen ZB332L is largely used for automotive components. Battery cases, cooling water compensation reservoirs, brake fluid reservoirs, wash water reservoirs, dashboard supports, luggage compartment trims and door trim panels are typical applications.
- In the electro-technical industries, Parslen ZB332L is used for appliances, cables and wires (e.g. as slotted core element in fibre optic cables.)



Typical Properties [a,b]	Method	Unit	Value(a)	Tolerance
Melt flow rate(230 ° C, 2.16 Kg)	ASTM D 1238	gr/10 min	10	± 0.7
Vicat softening point (9.8 N)	ASTM D 1525	° C	150	± 10
H.D.T. (0.46 Mpa)	ASTM D 648	° C	88	± 8
Flexural modulus	ASTM D 790	MPa	1200	± 120
Tensile strength at yield	ASTM D 638	MPa	27	± 4
Elongation at yield	ASTM D 638	%	9	± 1
Izod impact strength(notched) at 23° C	ASTM D 256	J/m	100	± 10
Izod impact strength(notched) at -20° C	ASTM D 256	J/m	40	± 4
Rockwell hardness [R – B Scale]	ASTM D 785	R – B	93	± 10

a) Values shown are averages and are not to be considered as exact product specifications.
b) All specimens are prepared by injection molding. (Last revised 10, Aug. 2011)



Parslen ZB332L is suitable for food contact.