

| Grade | MFI g/10 min | Density g/cm | Applications |
|----------------|--------------|--------------|--|
| Polynar SF-030 | 2.5-3.5 | 0.9 | Gunny bag fibers, Plastic connectors, Package requisites |
| Polynar F-040 | 3.8-4.8 | 0.9 | Injection instruments, Rope, Single spun threads |
| Polynar SF-060 | 5-7 | 0.9 | Gunny bag fiber, plastic belts, car appliances, plastic containers |
| Polynar SI-080 | 7.5-8.5 | 0.9 | Dual layered films, Multi spun threads, House furniture |
| Polynar FI-090 | 8.8-10.5 | 0.9 | Selfon. Toys, Packing instruments |
| Polynar FI-110 | 10.8-12.8 | 0.9 | Injection instruments (home appliances), Cloth of fitted carpet |
| Polynar YI-140 | 13.2-15.2 | 0.9 | Felt fitted carpet fiber, House furniture |
| Polynar FI-160 | 15.5-17.2 | 0.9 | Machine carpet fiber, Single Spun threads, Fitted carpet fiber |
| Polynar YI-180 | 17.5-19.5 | 0.9 | Cable hindrance coverage, Machine carpet fiber, Filter textile |
| Polynar YI-220 | 20-24 | 0.9 | Athletic clothes fiber, Medical instruments, Fitted and machine carpet fiber |