

Homopolymer Grades(Marun Petrochemical Company)

Grade	MFI ISO1133 (230c-2.16 Kg)	Application
X 30 G	9	Injection Moulding
X 30 S	9	Injection Moulding
YD 50G	0.3	Extrusion & THERMOFORMING
YF 39S	12	FIBRES
YS 32S	2	Extrusion & THERMOFORMING
YX 37F	9	Extrusion & THERMOFORMING
Z 21 S	25	FIBRES
Z 30 G	25	Injection Moulding
Z 30 S	25	FIBRES