

LDPE	LLDPE	MDPE	HDPE	PP	PVC	GPPC	HIPS	EPS	PET	ABS	SBR	PBR	PC	E.P.
------	-------	------	------	----	-----	------	------	-----	-----	-----	-----	-----	----	------



PVC-S۶۵۵۸

كوثر شیمی
Kosar Shimi
+9821 - 43462000
info@kosar.co
www.kosar.co

۱) Product Description:

PVC contains approximately ۵۶% by weight of chlorine. This polymer possesses thermoplastic properties. Grade S۶۵۵۸ has low porosity & high bulk density.

۲) Applications:

- Pipe and fittings
- Injection moulding

۳) Typical Data

Property	Unit	Value	Test Method
K-value		۶۵	DIN-۵۳۷۲۶
Sulphate ash	wt % max	۰.۰۵	DIN-۵۳۵۶۸/۲
Volatiles	wt % max	۰.۲	ISO R-۱۲۶۹
Bulk density	gr/li	۶۰۰	DIN-۵۳۴۶۶
Screen analysis (residue on sieve)			
> ۶۳ micron	wt % min	۹۰	DIN-۵۳۷۳۴
> ۲۵۰ micron	wt % max	۵	DIN-۵۳۷۳۴
Dark resin (particles in ۲۵۰ gr PVC)	No. max	۳۰	HULS-۶.۷
Plasticizer acceptance	grDOP/۱۰۰ grPVC min.	۱۰	DIN-۵۳۴۱۷/۱
Fish eyes	number per ۲۵ cm ^۲ max.	۵	HULS-۶.۹
Flowability (dia. of funnel outlet)	mm max.	۴	HULS-۶.۱۰
Viscosity number	Cm ^۲ /gr	۱۰۵	DIN-۵۳۷۲۶
Residual VCM	ppm	≤ ۱	HULS-۶.۱۱

* Typical Values : not to be construed as specifications

Producer: Bandar Imam Petrochemical Co.

Licensor: HULS

Packing: ۲۵ Kg plastic bag