

PVC PRODUCT SPECIFICATION & APPLICATION

جدول مشخصات و کاربرد انواع محصولات پی وی سی

Products	Properties	K-Value	Viscosity No.	Sulfate Ash	Volatiles	Bulk Density	Screen Ana. >63µm	Screen Ana. >250µm	Dark Resin Parti	P.A.*	Fish Eyes	F.D of F.O.**	APPLICATION موارد مصرف						
													WITH PLASTICIZER یا نرم کننده			WITHOUT PLASTICIZER بدون نرم کننده			
													EXTRUSION	INJECTION	CALANDERING	EXTRUSION	INJECTION	CALANDERING	
Polyvinyle Chloride (P.V.C) Poliran PV S.6058	Test Method	DIN-53726	DIN-53726	DIN-53568/2	ISO R-1269	DIN-53466	DIN-53734	DIN-53734	HULS-6.7	ASTM D.3367	HULS-6.9	HULS-6.10			برای تهیه کامپاندهای پلیمری	فیلم های شفاف ورق، روکش سیم و ...	تزریقی اتصالات کابیت برقی، قطعات ساختمان و ...	فیلم و کفپوش	
	Value	59-61	85-92	0.05 max	0.2 max	550-610	90 min	5 max	30 max	10 min	5 max	4 max	---	---	ADDITIVE POLYMER IN COMPOUNDS FOR CALANDERING	TRANSPARENT FILM HOLLOW WATER,ECT	INJECTION MOULDING BUILDING PARTS WATER FITTING,ECT	FILM & FLOORING MATERIAL	
	Units	--	cm3/gr	wt. %	wt. %	gr/lit	wt. %	wt. %	No./250 gr PVC	gr DOP/100 gr PVC	No./25 cm2	mm							
	Properties	K-Value	Viscosity No.	Sulfate Ash	Volatiles	Bulk Density	Screen Ana. >63µm	Screen Ana. >250µm	Dark Resin Parti	P.A.*	Fish Eyes	F.D of F.O.**							
Polyvinyle Chloride (P.V.C) Poliran PV S.6558	Test Method	DIN-53726	DIN-53726	DIN-53568/2	ISO R-1269	DIN-53466	DIN-53734	DIN-53734	HULS-6.7	ASTM D.3367	HULS-6.9	HULS-6.10					لوله های سخت	قطعات تزریقی، اتصالات و ...	
	Value	64-66	101-109	0.05 max	0.2 max	540-600	90 min	5 max	30 max	10 min	5 max	4 max	---	---			RIJID PIPES TRANSPARENT FILM,ECT	PARTS BY INJECTION MOULDING PARTS FITTING, ECT	
	Units	--	cm3/gr	wt. %	wt. %	gr/lit	wt. %	wt. %	No./250 gr PVC	gr DOP/100 gr PVC	No./25 cm2	mm							
	Properties	K-Value	Viscosity No.	Sulfate Ash	Volatiles	Bulk Density	Screen Ana. >63µm	Screen Ana. >250µm	Dark Resin Parti	P.A.*	Fish Eyes	F.D of F.O.**							
Polyvinyle Chloride (P.V.C) Poliran PV S.7054	Test Method	DIN-53726	DIN-53726	DIN-53568/2	ISO R-1269	DIN-53466	DIN-53734	DIN-53734	HULS-6.7	ASTM D.3367	HULS-6.9	HULS-6.10	شلیک اتصالات کابل ارتجعی روکش کابل و ...	تزریقی و ...	فیلم و کفپوش				
	Value	69-71	120-129	0.05 max	0.2 max	445-505	85 min	0.5 max	30 max	30 min	5 max	4 max	PIPES HOSES FLEXIBLE FITTING, FILM SHEET, CABLE WIRE COVER.	PARTS BY INJECTION MOULDING	FILM & FLOORING MATERIAL				
	Units	--	cm3/gr	wt. %	wt. %	gr/lit	wt. %	wt. %	No./250 gr PVC	gr DOP/100 gr PVC	No./25 cm2	mm							
	Properties	K-Value	Viscosity No.	Sulfate Ash	Volatiles	Bulk Density	Screen Ana. >63µm	Screen Ana. >250µm	Dark Resin Parti	P.A.*	Fish Eyes	F.D of F.O.**							