


# Tylose<sup>®</sup> HS 6000 YP2

Technical Data Sheet




Product properties			
Constitution:	Hydroxyethyl cellulose		
Etherification:	high etherification	Delayed solubility:	yes
Particle size:	powder	Biostability:	yes
Level of viscosity: according to Höppler	6000 mPa·s		

Recommended fields of application	
Interior paints	
Solid paints	
Exterior paints	
Tinters	
Distempers	
Glazes	
Gloss effect top coats	
Powder paints	

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should not therefore be construed as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our General Conditions of Sale.

# Tylose<sup>®</sup> HS 6000 YP2

## Technical Data Sheet



### Application performance

Gloss:	high	Thickening effect:	moderate
Pigment compatibility:	high	Wet scrub resistance:	moderate
Anti-Spattering:	good	Water retention:	moderate
Pseudoplasticity:	low		

### Packaging, Storage, Safety instructions

Like all fine-particle organic substances, cellulose ethers constitute a dust explosion hazard. Dust formation and deposits must be kept to a minimum so that no ignitable dust/air mixtures can form. Ignition sources such as naked flames, hot surfaces, sparks and static electricity should be avoided. Tylose starts to decompose at about 200°C. Its ignition temperature is >360°C. Tylose burns easily and the fire may spread.

When stored in closed containers, or in its original packaging in a dry place at room temperature, Tylose can be kept for a long time. In the case of high viscosity grades, a slow loss of viscosity can be measured after lengthy storage (>1 year). Tylose absorbs water from moist air. Once opened, container must be resealed and kept tightly closed.

This Tylose-type is supplied in multi-ply paper bags with polyethylene intermediate layer and/or in big bags.