

High Density Polyethylene

EX1



Typical properties	Test method (DIN)	Unit	Value
MFI@190°C, 5 kg	53735	gr/10min	1.6
Density	53479	gr/ml	0.944
Notched Impact Strength	53453	mj/mm²	_
Standard Yellow Index	6167	-	≤ 4

> Values shown are averages & are not to be considered as product specifications.



Certificate No.: CH98/8032

ISO 14001:2004 Certificate No.: CH03/0112

OHSAS 18001:1999 Certificate No.: CH05/0675

Main application & Characteristics:

distribution and good processing properties, suitable for film extrusion applications.

- Typical applications are;
 - Tubular and flat films
 - Stretched film tape
- * EX1 is suitable for food contact.

