



Grade/Product Name : HF4760(THE/THT:Grade)

کوثر شیمی

Kosar Shimi

+9821 - 43462000

info@kosar.co

www.kosar.co

Test/Composition	value	Unit	Method
Density	0.95 6 ±0.002	g/cm ³	ISO 1183
MFR(190°/21.16)	23±4	g/10min	ISO 1133
MFR(190°/5)	1.2±0.3	g/10min	ISO 1133
Notched Impact (23°C) ²	≥9	mJ/mm ²	ISO179/1eA

Main Application: Small blow moulding

Notes:

- 1- FRR values are statistical and calculated by dividing MFR values.
- 2- Notch Impact Test specimen from compressed moulded sheet 23°C and The data quoted is average values