## **Jampilen HP500N**

Homopolymer

**Description:** 





"Jampilen HP500N" is a medium fluidity polypropylene homopolymer for general purpose injection molding applications. Due to its good flow properties, this grade offers easy mold filling and short cycle times. Articles produced from "Jampilen HP500N" exhibit good dimensional stability and high stiffness. "Jampilen HP500N" is widely used for injection molding consumer goods such as food containers, cool boxes, vacuum flasks, flower pots, toys, garden furniture and small appliances. In the medical sector, "Jampilen HP500N" is used for 3-part syringes and a wide range of health-care items. Other applications are closures, caps and crates for products. "Jampilen HP500N" is suitable for food contact. oversing Method: Injection molding Easy mold filling and short cycle times Good dimensional stability High stiffness Homorolymer **Typical Applications** Cool boxes, vacuum flasks, flower pots Food eentainers Carden furniture Toys 3-part syringes Closure <u>can</u> Crates **Approval:** Food **TYPICAL PROPERTIES** VALUE 1/N/T METHOD Physical Melt Flow Rate (230 °C, 2.16kg) g/10min A/ST/M D1238 12 ASTM D1505 0.9 Density g/cm<sup>3</sup> **Mechanical** 1550 MPa ASTM D790 Flexural Modulus Tensile Strength at Yield 34 MPa ASTM D638 Tensile Elongation at Yield 12 % ASTM D638 Izod Impact Strength (notched) at 23 °C 30 ASTM D256 J/m **Rockwell Hardness** 102 R Scale ASTM D785 Thermal Vicat softening point (10N) °C 154 **ASTM D1525** °C H.D.T. (0.46 Mpa) 95 ASTM D648 Accelerated oven ageing in air at 150 °C 360 hours ASTM D3012

NAMPIC VOISTEN

This data and information is considered to be correct and offered in good faith as a guide. But we do not warrant or otherwise guarantee the merchantability, fitness for a particular purpose or suitability of this information, products or processes described.