



HD-BL 3 License Grade Code HF 4760(THT)

كوثر شيمي
Kosar Shimi
+9821 - 43462000
info@kosar.co
www.kosar.co

Product Description:

"BL3" is a high density polyethylene with 1-Butene as co monomer. It is high density and stiffness, good ESCR, high rigidity, good flowability and impact strength.

Applications:

- Small blow moulding
- Bottles
- Containers (up to 5 lit)
- Packaging of pharmaceuticals & surfactants

Typical data

PROPERTY	TEST METHOD	UNIT	TYPICAL VALUE*
Mass density (23 C)	ISO 1183	g/cm ³	0.954
Melt Flow Rate (190 C/5.06kg)	ISO 1133	g/10min	1.2
Melt Flow Rate (190 C/21.16kg)	ISO 1133	g/10min	23
FRR(21.6/5)		-	19
Impact strength (23 C)	ISO 179/1eA	mj/mm ²	10
Swell ratio	MPC-Test	%	120

- Typical value not to be constructed as specifications.
- Recommended melt temp. 180-220 c