

HD-I3 License Grade Code HC 7260(THE)

دوتر شیـمی Kosar Shimi +9821 - 43462000 info@kosar.co www.kosar.co

Product Description:

"13" is a high density polyethylene with 1-Butene as co pronomer. It is rigid, low warpage, good flowability, high density hardness and sttifness, good impact strength good stress/cracking resistance.

Applications/

- Injection moulding
- Orates
- Engineering parts
- Olosures

Typical data

PROPERTY	TEST METHOD	UNIT (TYTICAL YALVE*
Mass density (23 C)	ISO 1183	g/cm3	0.957
Melt Flow Rate (190 C/2.16kg)	ISO 1133	g/10min	9
Melt Flow Rate (190 C/5 kg)	ISO 1133	g/10min	23
FRR(21.6/5)		-	2.8
Impact strength (23 C)	ISO 179/1eA	mj/mm2	2.5

- Typical value not to be constructed as specifications.
- Recommended injection moulding temp. 200-280 c.

